

Tapa flexible PET · 40 µm

Alta barrera · Sellado pelable sobre PET

FILM DE TAPA FLEXIBLE DE PET DE ALTA BARRERA SELLABLE SOBRE PET

DESCRIPCIÓN: TAPA flexible de PET con alta barrera al O2

USOS: No termoformable. Sellado pelable sobre PET. Envasado en atmósfera modificada (MAP)

ESTRUCTURA · SECUENCIA DE CAPAS



PROPIEDADES FÍSICAS / QUÍMICAS

DESCRIPCIÓN	VALOR	MÉTODO
ESPESOR	40 µm	Método interno
PESO	52 g/m²	Método interno
TASA DE TRANSMISIÓN DE O2	1.1 cc/m²/24h @1 bar	ASTM D3985
TASA DE TRANSMISIÓN DE VAPOR DE H2O	0.9 g/m²/24h @1 bar	ASTM F1249
RANGO DE TEMPERATURA DE SELLADO	140 – 180 °C	Método interno

ALMACENAMIENTO

PROPIEDAD	CONDICIONES TÉCNICAS
CONDICIONES DE ALMACENAMIENTO	En almacén seco, bien cubierto, con temperaturas entre 5 y 35 ° C y humedad recomendada del 40% al 70%. Si el material recibido no se encuentra en estas condiciones, mantenerlo a temperatura ambiente durante 24 horas antes del uso
DURACIÓN	MÁX 1 año desde la fecha de producción indicada en las etiquetas

Tapa flexible PET · 40 µm

Alta barrera · Sellado pelable sobre PET

ETIQUETADO AMBIENTAL

CÓDIGO DE RECICLAJE (Dir. 94/62/CE)	RECOGIDA SELECTIVA*
	PLÁSTICO

* Para la recogida selectiva, consulte la normativa local

CUALIFICACIÓN DEL PRODUCTO

Dadas las numerosas posibilidades de transformación y uso del producto, es esencial realizar pruebas de cualificación bajo la exclusiva responsabilidad del usuario.

CONTACTO ALIMENTARIO · DOCUMENTACIÓN

Para los detalles de conformidad de contacto alimentario, consulte la Declaración de Conformidad (DoC) correspondiente.

Datos y métodos reproducidos de la ficha técnica del producto. No constituyen ensayos ni certificaciones propios de MOLTHIS.

Flexible PET lid · 40 µm

High barrier · Peelable sealing on PET

FLEXIBLE TOP FILM IN PET HIGH BARRIER SEALABLE ON PET

DESCRIPTION: Flexible TOP in PET with high O₂ Barrier

USES: Non Forming. Peelable sealing on PET. Modified Atmosphere Packaging (MAP)

STRUCTURE · LAYER SEQUENCE



PHYSICAL / CHEMICAL PROPERTIES

DESCRIPTION	VALUE	METHOD
THICKNESS	40 µm	Internal Method
WEIGHT	52 g/m ²	Internal Method
O ₂ TRANSMISSION RATE	1.1 cc/m ² /24h @1 bar	ASTM D3985
H ₂ O VAPOR TRANSMISSION RATE	0.9 g/m ² /24h @1 bar	ASTM F1249
SEALING TEMPERATURE RANGE	140 – 180 °C	Internal Method

STORAGE

PROPERTY	TECHNICAL CONDITIONS
STORAGE CONDITIONS	In dry warehouse, well covered, with temperatures between 5 and 35 ° C and suggested humidity from 40% to 70% If the material received is not in these suggested conditions, please keep it at room temperature for 24 hours before use
DURATION	MAX 1 year from the production date on the labels

Flexible PET lid · 40 µm

High barrier · Peelable sealing on PET

ENVIRONMENTAL LABELLING

RECYCLING CODE (Dir. 94/62/CE)	WASTE SORTING*
	PLASTIC

* For the waste sorting refer to local legislation

PRODUCT QUALIFICATION

Given the many possibilities of processing and use of the product, it is essential for qualification tests to be conducted under the sole responsibility of the user.

FOOD CONTACT · DOCUMENTATION

For food-contact compliance details, consult the relevant Declaration of Conformity (DoC).

Data and methods reproduced from the product technical data sheet. They do not constitute MOLTHIS's own tests or certifications.